

LLC "KASTAMONU INTEGRATED WOOD INDUSTRY"			PRODUCT	BRN32TV- 961- 8X195X1380	
Control settings	Standard	Measurement unit	Tolerance Range	Test results	
Thickness	EN 13329	mm.	t max. - t min. ≤ 0,5	7,67	
Density	EN 323	kg/m ³	880 ± 10	887,27	
Width	EN 13329	mm.	w max. - w min. ≤ 0,2	195,01	
Length	EN 13329	mm.	Δl ≤ 0,5	1380	
Rectangularity	EN 13329	mm.	Max. 0,2	0	
Straightness	EN 13329	mm.	< 0,414 mm	0	
Width flatness	convexity, not more than	EN 13329	mm.	< 0,390 mm	0
	concavity, not more than	EN 13329	mm.	< 0,292 mm	0
Length flatness	convexity, not more than	EN 13329	mm.	< 13,80 mm	0
	concavity, not more than	EN 13329	mm.	< 6,90 mm	1,34
Resistance to abrasion	EN 13329	turnovers	≥ 4000	4200	
Abrasion class	EN 13329	class	≥ AC4	AC4	
Impact resistance	EN 13329	class	≥ IC2	IC2	
Resistance to staining	EN 14323	score	not less than 5	5	
Resistance to a smoldering cigarette	EN 14323	score	not less than 4	4	
Thickness swelling	EN 13329	%	≤ 18	12,88	

Chief of department quality and certification



Svetlana Klymenko/